

ABS @df

ABS @df is an extra strong impact-resistant filament ideal for 3D printing of solid printed products. Due to the process stability and physical features of Acrylonitrile Butadiene Styrene it is a widely used thermoplastic polymer in industry. The material is also very light and durable. This makes ABS @df particularly suitable for tools, toys and all kinds of utensils. Printed at a slightly over-average temperature for ABS, this filament gives extra strong 3D print results.

Features:

- Very high impact-resistance
- Extra strong
- Stable printing
- Light and durable
- Limited warping



Colours:

ABS @df is available from stock in 25 bright colours. Other colours on request



Packaging:

ABS @df is available in nearly any type of packaging and labelling. Ask our team to help you customizing your product.

Filament specs.

Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,03 g/cc
MFR 220°C/10 kg	ISO 1133	5,5 cm ³ /10 min
Tensile strength at yield	ISO 527	44 Mpa
Elongation at break	ISO 527 1/2	9%
Tensile modulus	ISO 527	2000 Mpa
Impact strength - Charpy method 23°C	ISO 179	35 kJ/m ²
Printing temp.	DF	220-260°C
Melting temp.	ISO 294	245°C ± 10°C
Vicat softening temperature	ASTM D 1525	103°C

Additional info:

Recommended temperature for heated bed is ± 90-110°C.

ABS @df is printed at a slightly higher temperature to make the final product extra strong.

ABS @df can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.